



US009950749B2

(12) **United States Patent**
Webb et al.

(10) **Patent No.:** **US 9,950,749 B2**

(45) **Date of Patent:** **Apr. 24, 2018**

(54) **HYBRID COMPOSITE INSTRUMENT PANEL**

25/14 (2013.01); *B29K 2105/12* (2013.01);

B29L 2031/3008 (2013.01)

(71) Applicant: **Ford Global Technologies, LLC**,
Dearborn, MI (US)

(58) **Field of Classification Search**

CPC *B60K 37/00*; *B62D 25/14*; *B29C 43/003*;

B29C 43/02; *B29C 47/0004*

See application file for complete search history.

(72) Inventors: **Jeff Webb**, Iron Mountain, MI (US);
Kalyanaraman Bharathan, Canton, MI
(US); **Tim Beard**, Perry, MI (US)

(56) **References Cited**

(73) Assignee: **Ford Global Technologies, LLC**,
Dearborn, MI (US)

U.S. PATENT DOCUMENTS

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

3,950,483 A * 4/1976 Spier *B29C 45/164*

264/241

4,884,778 A 12/1989 Yamamoto

(Continued)

(21) Appl. No.: **14/855,877**

FOREIGN PATENT DOCUMENTS

(22) Filed: **Sep. 16, 2015**

DE 3806783 A1 9/1989

DE 102008021103 A1 10/2009

(Continued)

(65) **Prior Publication Data**

US 2016/0059905 A1 Mar. 3, 2016

Related U.S. Application Data

Primary Examiner — James A English

(74) *Attorney, Agent, or Firm* — Vichit Chea; Price
Heneveld LLP

(63) Continuation of application No. 14/270,951, filed on
May 6, 2014, now Pat. No. 9,186,993.

(51) **Int. Cl.**

B62D 25/14 (2006.01)

B29C 45/00 (2006.01)

B62D 29/04 (2006.01)

B60K 37/00 (2006.01)

B29C 45/16 (2006.01)

B62D 25/06 (2006.01)

B29L 31/30 (2006.01)

B29K 105/12 (2006.01)

(52) **U.S. Cl.**

CPC *B62D 29/043* (2013.01); *B29C 45/0005*


(2013.01); *B29C 45/16* (2013.01); *B60K 37/00*

(2013.01); *B62D 25/06* (2013.01); *B62D*

(57) **ABSTRACT**

A vehicular instrument panel having a reinforcement that includes a plurality of chopped carbon fibers within a nylon resin, and a substrate coupled to the reinforcement comprising a plurality of chopped carbon and chopped glass fibers within a nylon resin. The plurality of chopped carbon and glass fibers in the substrate are segregated such that the carbon fibers and the glass fibers are each substantially concentrated within respective driver-side and passenger-side portions of the substrate. The substrate can also include a boundary region such that the plurality of chopped carbon and glass fibers in the substrate are substantially mixed in the boundary region.

8 Claims, 6 Drawing Sheets



References Cited

2006/0081612	A1	4/2006	Kuntz	
2006/0097539	A1	5/2006	Noisternig et al.	
2008/0057285	A1	3/2008	Polk	
2008/0098655	A1	5/2008	Valentage	
2008/0315612	A1	12/2008	D'Alessandro	
2009/0309260	A1	12/2009	Keuchel	
2011/0233955	A1	9/2011	Utsugi et al.	
2013/0052412	A1*	2/2013	Fox	B29C 43/02 428/139
2013/0082416	A1*	4/2013	Wakeman	B29C 33/14 264/259
2013/0249242	A1	9/2013	Kimoto et al.	
2013/0257120	A1	10/2013	Tracht et al.	
2014/0178652	A1*	6/2014	Gross	B29C 70/46 428/189
2015/0115580	A1	4/2015	Gould et al.	

FOREIGN PATENT DOCUMENTS

2002/0135161	A1 *	3/2015	Carter		
		9/2002	Lamb		B29C 43/003 280/728.3
2006/0051569	A1	3/2006	Porter et al.		
2006/0057319	A1 *	3/2006	Gleich		B29C 47/0004 428/35.2

EP	0083701	A2	7/1983
WO	0170558	A1	9/2001
WO	2013072021	A1	5/2013

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5A





FIG. 5B

**FIG. 6**

1

HYBRID COMPOSITE INSTRUMENT PANEL**CLAIM OF PRIORITY**

The present application is a continuation application that claims priority to and the benefit under 35 U.S.C. § 120 of U.S. patent application Ser. No. 14/270,951 filed on May 6, 2014, entitled "HYBRID COMPOSITE INSTRUMENT PANEL," now issued as U.S. Pat. No. 9,186,993, the entire disclosure of which is hereby incorporated herein by reference.

FIELD OF THE INVENTION

The present disclosure generally relates to composite component designs, and more particularly relates to composite vehicular instrument panel designs and methods for making the same.

BACKGROUND OF THE INVENTION

It is becoming more common for vehicles to utilize lightweight components and designs in order to decrease vehicle weight, particularly in large, interior vehicle components such as instrument panels. Weight reductions can increase vehicle performance and fuel economy. Weight savings may be realized by substituting current materials of vehicle components with lighter weight materials. However in some cases, lighter weight materials employed in vehicles can have less mechanical integrity than their heavier weight counterparts.

In other cases, certain lighter weight materials, such as carbon fiber composites, can actually have improved mechanical performance over conventional materials. Unfortunately, the manufacturing costs of making vehicular components with these materials can be prohibitive or at least not low enough to offset the potential improvements in vehicle performance and fuel economy. Further, these stronger composite materials are often employed in large vehicular components that have only one or a handful of regions that actually require elevated mechanical performance.

Accordingly, there is a need for lighter-weight vehicular components having better or comparable mechanical performance when compared to conventional vehicular components. There is also a need to tailor the mechanical properties in particular regions within these components for the particular application, thus minimizing the use of expensive reinforcing materials and maximizing mechanical property enhancements where it is required in the component.

SUMMARY OF THE INVENTION

According to one aspect of the present disclosure, a vehicular instrument panel includes a panel element comprising chopped carbon and chopped glass fibers within a nylon resin. The fibers are segregated such that the carbon and glass fibers are each substantially concentrated within respective driver-side and passenger-side portions of the element. Further, the panel comprises a boundary region in the driver-side or the passenger-side portion having a mixture of the carbon and glass fibers.

According to another aspect of the present disclosure, a vehicular component includes a first portion comprising a first, chopped fiber material within a first resin; a second portion comprising a second, chopped fiber material within a second resin; and a plurality of boundary regions, each region between the first and second portions and having a

2

mixture of the first and second fiber materials within the first and second resins. Further, the vehicular component is inside or on a vehicle.

According to a further aspect of the present disclosure, a vehicular component includes a first portion comprising a first, chopped fiber material within a first resin; a second portion comprising a second, chopped fiber material within a second resin; and a boundary region between the first and second portions having a mixture of the first and second fiber materials within the first and second resins. Further, the vehicular component is inside or on a vehicle.

These and other aspects, objects, and features of the present invention will be understood and appreciated by those skilled in the art upon studying the following specification, claims, and appended drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

In the drawings:

FIG. 1 is a front perspective view of a vehicular instrument panel within a vehicle according to one embodiment; FIG. 2 is an exploded top perspective view of the instrument panel depicted in FIG. 1;

FIG. 3 is a bottom elevational view of a vehicular component according to a further embodiment;

FIG. 4 is a top perspective view of an injection molding system according to an additional embodiment;

FIG. 5A is a cross-sectional view of the injection molding system of FIG. 4 during a step of injecting molten composites into a mold, taken at line X-X;

FIG. 5B is a cross-sectional view of the injection molding system of FIG. 4 during a step of cooling the melted composites, taken at line X-X; and

FIG. 6 is a schematic of a method for forming a vehicular component using the injection molding system of FIG. 4 according to another embodiment.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

For purposes of description herein, the terms "upper," "lower," "right," "left," "rear," "front," "vertical," "horizontal," and derivatives thereof shall relate to the disclosure as oriented in FIG. 1. However, it is to be understood that the disclosure may assume various alternative orientations, except where expressly specified to the contrary. It is also to be understood that the specific devices and processes illustrated in the attached drawings, and described in the following specification are simply exemplary embodiments of the inventive concepts defined in the appended claims. Hence, specific dimensions and other physical characteristics relating to the embodiments disclosed herein are not to be considered as limiting, unless the claims expressly state otherwise.

Referring to FIG. 1, a cabin 10 of a vehicle 14 is depicted. The vehicle 14 includes a driver-side region 18 and a passenger-side region 22. Inside the cabin 10 is an instrument panel 26, among other vehicle components, such as a windshield 36. The instrument panel 26 is located vehicle forward in the cabin 10 beneath the windshield 36. The instrument panel 26 has a driver-side portion 40, a center-stack portion 44, and a passenger-side portion 48. These portions of the instrument panel 26, and particular regions or locations within them, often have differing mechanical property requirements.

As used in this disclosure, "outboard" refers to the lateral sides or regions most proximate to a driver-side door 52 and

3

a passenger-side door 56 in the vehicle 14. The term “inboard” as used in this disclosure refers to a central area in the vehicle 14 inboard from the laterally opposing outboard sides or regions.

The driver-side and passenger-side portions 40, 48 of the instrument panel 26 are in substantial proximity to respective driver-side and passenger-side regions 18, 22 of the vehicle 14. The driver-side portion 40 of the instrument panel 26 includes an instrument cluster 60 covered by an instrument cluster hood 64. Located below the instrument cluster 60 is a steering column 68. The steering column 68 is supported by the instrument panel 26 and engages a steering system (not shown) vehicle forward of the instrument panel 26. The steering column 68 extends from the steering system into the cabin 10 through the instrument panel 26. The steering column 68 has a steering wheel 72 disposed in the cabin 10 in the driver-side region 18 of the vehicle 14. The steering wheel 72 includes a driver airbag 76 which deploys upon a vehicle collision event. As such, the driver-side portion 40 of the instrument panel 26 can have demanding mechanical requirements, particularly at locations where it must support other vehicular components subject to variable loads and motion, e.g., steering column 68.

Still referring to FIG. 1, disposed on each outboard side of the instrument panel 26 is a side air vent 80. The instrument panel 26 also incorporates a set of central air vents 84 located in the center-stack portion 44 of the instrument panel 26. The center-stack portion 44 of the instrument panel 26 is located between the driver-side portion 40 and the passenger-side portion 48. The center-stack portion 44 includes an interface 88 that is operable by occupants of both the driver-side and the passenger-side regions 18, 22 of the vehicle 14. The center-stack portion 44 is connected to both the driver-side portion 40 and the passenger-side portion 48 of the instrument panel 26.

As also depicted in FIG. 1, the passenger-side portion 48 of the instrument panel 26 includes a glove box assembly 110, and a passenger airbag assembly 114 that is located above the assembly 110. The glove box assembly 110 includes a glove box door 118 permitting access to a glove box bin (not shown). In some embodiments, the glove box assembly 110 is a separate component from the instrument panel 26 and is inserted and attached during manufacturing. In other embodiments, the glove box bin of the assembly 110 is integrally formed from an instrument panel substrate 120 (FIG. 2) of the instrument panel 26 and the glove box door 118 is a separate component that is attached during manufacturing. Depending on the configuration of passenger side portion 48, it may have central regions or locations that require additional mechanical reinforcement, such as where it contains or attaches to glove box assembly 110.

Referring again to FIG. 1, the passenger airbag assembly 114 includes a passenger airbag chute 124 (FIG. 2), and other components such as a passenger airbag, an airbag canister, and an inflator. During a vehicle collision event, the passenger airbag is inflated by the inflator (not shown), thereby causing the passenger airbag to expand from the canister through the passenger airbag chute 124 (FIG. 2) and out of the instrument panel 26. The inflation and expansion of the airbag generates high stresses in surrounding components which can lead to structural failure of the instrument panel 26 if not properly reinforced. In some embodiments, the instrument panel substrate 120 (FIG. 2) of the instrument panel 26 may also include knee airbag canisters for the occupants of both the driver-side and passenger-side regions 18, 22, potentially necessitating additional reinforcement.

4

Referring now to FIG. 2, the instrument panel 26 includes the instrument panel substrate 120 and a reinforcement 150. The reinforcement 150 is located vehicle forward of the substrate 120 and is coupled to the substrate 120 at multiple points. The substrate 120 and the reinforcement 150 may be coupled via adhesive bonding, vibration welding, hot plate welding, or other forms of joining. The reinforcement 150 includes a driver-side portion 154, a center-stack portion 158, and a passenger-side portion 162. The reinforcement 150 defines a steering column aperture 166 and a glove box aperture 170 on the respective driver-side and passenger-side portions 154, 162. Flanges 174 are located within the center-stack portion 158 of the reinforcement 150 and extend vehicle rearward to engage and couple with a center-stack portion 180 of the substrate 120.

As also depicted in FIG. 2, the instrument panel substrate 120 includes a driver-side portion 184, the center-stack portion 180, and a passenger-side portion 188. The driver-side portion 184 of the substrate 120 defines a steering column opening 192 which aligns with the steering column aperture 166 of the reinforcement 150 when the substrate 120 and the reinforcement 150 are coupled. The steering column 68 (FIG. 1) passes through both the steering column aperture 166 and the steering column opening 192, and is attached to the substrate 120 via a steering column mounting area 196, as shown in FIG. 2. The steering column mounting area 196 is located on the substrate 120 proximate to the steering column opening 192. In some embodiments, a jacket for the steering column 68 may be integrally formed in the substrate 120 proximate to the mounting area 196. In other embodiments, a mounting bracket or a support bracket may be integrally formed in the substrate 120 proximate to the steering column opening 192 for supporting the steering column 68. The coupling of the reinforcement 150 to the substrate 120 provides sufficient strength for the mounting area 196, and ultimately the instrument panel 26, to support the weight of the steering column 68 without the use of a cross-car beam. As such, certain regions or locations in the driver-side portion 184 of the substrate 120 may require and/or benefit from additional reinforcement.

Still referring to FIG. 2, the center-stack portion 180 of the instrument panel substrate 120 includes an electronics bay 200 for housing and mounting the interface 88 (FIG. 1) as well as other electronic components. The center-stack portion 180 is located between and is integrally connected to both the driver-side and passenger-side portions 184, 188 of the substrate 120. Depending on the electronic components and other components deployed in the center-stack portion 180, additional localized reinforcement in the substrate 120 with hybrid composites in these regions could provide mechanical performance and/or weight savings benefits.

The passenger-side portion 188 of the instrument panel substrate 120 defines a glove box opening 204 and a passenger airbag assembly opening 208 for housing the respective glove box assembly 110 (FIG. 1) and passenger airbag assembly 114 (FIG. 1). In some embodiments, the substrate 120 may be configured to further define a glove box bin and/or an airbag canister as integral bodies that extend from the respective glove box and passenger airbag assembly openings 204, 208. In other embodiments, the reinforcement 150 could be configured to define a glove box bin and/or an airbag canister. The substrate 120 and the reinforcement 150 can also be configured to define knee airbag canisters.

As also depicted in FIG. 2, a duct 212 is located between the instrument panel substrate 120 and the reinforcement 150. The duct 212 conveys air when bonded to the rein-

5

forcement **150**. The air travels through the duct **212** to a set of substrate vent openings **216** which direct the air to the side and central air vents **80**, **84** of the instrument panel **26** (FIG. 1). Attached to the reinforcement **150** is a plenum bracket **220** which connects with a firewall (not shown) of the vehicle **14**. The plenum bracket **220** prevents bending of the instrument panel **26** in a vehicle forward and rearward direction. The plenum bracket **220** can also provide additional support for the steering column **68** (FIG. 1), coupled to the substrate **120**.

Referring again to FIG. 2, the instrument panel substrate **120** is formed from a hybrid composite material according to an embodiment of this disclosure. In one exemplary embodiment, the driver-side portion **184** can be formed from a nylon resin having chopped carbon fibers disposed in the resin. The passenger-side portion **188** can be formed from a nylon resin having chopped glass fibers disposed in the resin. In general, regions in the substrate **120** with higher percentages of chopped carbon fibers can have enhanced mechanical properties (e.g., toughness, tensile strength, fatigue resistance). The carbon fiber volume fraction and the glass fiber volume fraction in the passenger-side and driver-side portions **184**, **188** may be between about 1% and about 60%, preferably between about 15% and about 40%, and more preferably between about 30% to about 40%. In some embodiments, the fiber volume fraction in the driver-side portion **184** may be different from the fiber volume fraction in the passenger-side portion **188** of the substrate **120**. In additional embodiments, areas of the substrate **120** that are anticipated to encounter high stresses are configured to incorporate higher fiber volume fractions of chopped carbon fibers than areas not expected to experience high stresses. For example, the mounting area **196** may incorporate a higher fiber volume fraction, particularly of chopped carbon fibers, than the rest of the driver-side portion **184** of the substrate **120** to aid in supporting the steering column **68**. In another example, the surfaces of the instrument panel substrate **120** and reinforcement **150** subject to high stress during airbag deployment may incorporate higher fiber volume fractions. In further embodiments, the driver-side and passenger-side portions **184**, **188** of the substrate **120** may incorporate more than two composite materials.

In some embodiments, the fibers employed in the driver-side and passenger-side portions **184**, **188** of the instrument panel substrate **120** can be composed of materials including carbons, aramids, aluminum metals, aluminum oxides, steels, borons, silicas, silicon carbides, silicon nitrides, ultra-high-molecular-weight polyethylenes, A-glasses, E-glasses, E-CR-glasses, C-glasses, D-glasses, R-glasses, and S-glasses. Driver-side and passenger-side portions **184**, **188** may also incorporate more than one type of fiber. In some embodiments, the length of the chopped fibers can be between about 3 mm and about 11 mm, and more preferably between about 5 mm and about 7 mm. Typically, the fibers are randomly oriented in the resins within the driver-side and passenger-side portions **184**, **188**. However, they may also be substantially aligned directionally in areas of the substrate **120** subject to high directional stresses. Further, the resins employed in the driver-side and passenger-side portions **184**, **188** can comprise a nylon, a polypropylene, an epoxy, a polyester, a vinyl ester, a polyetheretherketone, a poly(phenylene sulfide), a polyetherimide, a polycarbonate, a silicone, a polyimide, a poly(ether sulfone), a melamine-formaldehyde, a phenol-formaldehyde, and a polybenzimidazole, or combinations thereof. In some embodiments, the resin of the driver-side portion **184** may be different from the resin employed in the passenger-side portion **188** of the

6

substrate **120**. It should also be understood that the reinforcement **150** and its driver-side, center-stack and passenger-side portions **154**, **158**, **162** can be fabricated with hybrid composite materials comparable to those described above in connection with substrate **120**. For example, the driver-side portion **154** of the reinforcement **150** can be formed from a nylon resin having chopped carbon fibers disposed in the resin. The passenger-side portion **162** can be formed from a nylon resin having chopped glass fibers disposed in the resin. Further, the volume fraction of the fibers in the resins, preferably the chopped carbon fibers, may be greater in areas subject to higher stress levels than in the rest of the reinforcement **150**.

Still referring to FIG. 2, the chopped carbon and glass fibers are segregated in the substrate **120** of the instrument panel **26** such that the carbon fibers are substantially concentrated in the driver-side portion **184** of the substrate **120** and the glass fibers are substantially concentrated in the passenger-side portion **188** of the substrate **120**. In general, the center-stack portion **180** of the substrate **120** is composed of both chopped carbon and glass fibers. In some embodiments, the center-stack portion **180** may primarily include carbon fibers, or primarily glass fibers. In other embodiments, the carbon fibers primarily contained in the driver-side portion **184** may also partially occupy the passenger-side portion **188** of the substrate **120**. In further embodiments, the carbon fibers primarily in the driver-side portion **184** may also occupy portions of the substrate **120** which are subject to high stress, regardless of passenger-side or driver-side orientation. For example, airbag deployment surfaces located in or on the substrate **120** or reinforcement **150** can include higher percentages of carbon fibers for additional mechanical reinforcement. The segregation of the fibers, e.g., chopped carbon and glass fibers, in the substrate **120** allows the higher strength fiber, e.g., carbon fiber, to be selectively used where there are particular high strength needs for the substrate **120**, such as to support the steering column **68**. The selective use of high percentages of carbon fibers based on driver/passenger orientation relative to the vehicle **14** allows a cost savings by efficiently using the more expensive carbon fibers only where needed.

As also shown in FIG. 2, a boundary region **240** can exist in some embodiments at the interface between the driver-side and passenger-side portions **184**, **188** of the instrument panel substrate **120**. The boundary region **240** includes a mixture of both types of fibers and resin(s) employed in the driver-side and passenger-side portions **184**, **188** of the substrate **120**. The mixing of fibers within the boundary region **240** ensures that an integral connection exists between portions of the substrate **120** composed of different composite materials. In one embodiment, the boundary region **240** may span or otherwise encompass the entire center-stack portion **180** of the substrate **120**. In another embodiment, the boundary region **240** may be present only between the center-stack and passenger-side portions **180**, **188**, or between the driver-side and center-stack portions **184**, **180** of the substrate **120**. The boundary region **240** can also be located anywhere in the substrate **120** where there is an interface between portions of the substrate **120** containing differing fiber fractions, fiber types and/or resins. In one exemplary embodiment, driver-side portion **184** may have an approximate 30% to 40% volume fraction of chopped carbon fibers in a resin, the passenger-side portion **188** may have an approximate 30% to 40% volume fraction of chopped glass fibers in the resin, and the center-stack portion **180** or the boundary region **240** may have an approximate 15% to 20% volume fraction of chopped carbon fibers and

an approximate 15% to 20% volume fraction of chopped glass fibers in the resin. In this configuration, the driver-side portion **184** is particularly reinforced with higher percentages of chopped carbon fibers relative to other portions of the substrate **120**.

According to some embodiments, the instrument substrate **120** and/or the reinforcement **150** of the instrument panel **26** may incorporate one or more preformed fiber mats in addition to the portions containing chopped fibers in a resin or resins. The preformed fiber mats may include woven or non-woven fibers that are held together using the same or different resins as employed in the driver-side and passenger-side portions **184**, **188** of the substrate **120**. The mats may also incorporate fibers having different dimensions from the fibers employed in the driver-side and passenger-side portions **184**, **188** of the substrate **120**. Similarly, the fibers of the mats may be in either a continuous or chopped configuration. The fibers of the mats may also be composed of a material having the same or a different composition from that of the fibers employed in the driver-side and passenger-side portions **184**, **188** of the substrate **120**. The mats may be incorporated in areas of the substrate **120** and/or the reinforcement **150** having high or low fiber volume fractions. Multiple mats may be used and layered in varying orientations in order to further enhance the mechanical properties of the substrate **120** and/or reinforcement **150** at particular locations. Exemplary locations in the substrate **120** for placement of the mat include, but are not limited to: the steering column mounting area **196**, airbag assembly opening **208**, glove box opening **204**, coupling locations between the reinforcement **150** and the substrate **120**, and other locations anticipated to experience higher stress levels compared to stresses in other areas of the substrate **120**.

The utilization of a hybrid composite containing carbon fibers in the substrate **120** and the reinforcement **150** permits the vehicle **14** to be designed and manufactured without a cross-car beam. Conventional cross-car beams are thick metal components traditionally used to support the instrument panel **26** and the steering column **68** of the vehicle **14**. In addition to adding significant weight to the vehicle **14**, the cross-car beam occupies a potential storage space behind the instrument panel **26** and obstructs placement of the passenger airbag assembly and the glove box assembly **110**. Without the cross-car beam, the vehicle **14** can achieve greater fuel efficiency as well as enhanced design freedom for the instrument panel **26** and its subassemblies.

Referring now to FIG. 3, the foregoing aspects of the instrument panel substrate **120** and reinforcement **150** (see FIGS. 1 and 2 and the corresponding description) can extend to other components, such as a vehicular component **250**. Here, component **250** has a first portion **254** comprising a first fiber material **258** within a first resin **262**. The component **250** also has a second portion **266** including a second fiber material **270** within a second resin **274**. Between the first and second portions **254**, **266** of the component **250** is a component boundary region **278** having a mixture of the first and second fiber materials **258**, **270** within the first and second resins **262**, **274**. The first and second portions **254**, **266** can be in substantial proximity to respective passenger-side and driver-side regions **18**, **22** (FIG. 1). As depicted schematically in FIG. 3, component **250** can be a headliner for the cabin **10** of the vehicle **14**. But it should be understood that component **250** may be another component located inside or on the vehicle **14** (FIG. 1) suitable for fabrication from a hybrid composite according to the foregoing principles. The first and second fiber materials **258**, **270** of the component **250** may be selected from the same

group of fibers employed in the substrate **120**. Further, the first and second fiber materials **258**, **270** employed in the first and second portions **254**, **266** may have the same or comparable fiber length and fiber volume fractions as the driver-side and passenger-side portions **184**, **188** of the substrate **120**. Similarly, the first and second resins **262**, **274** of the component **250** can have a composition comparable to the resin or resins employed in the substrate **120**. Further, the component **250** may incorporate a fiber mat comparable to the fiber mat described earlier in connection with the substrate **120**.

Referring now to FIG. 4, an injection molding system **300** is depicted that includes a heater **302**, a pump **304**, a controller **308**, a mold **312**, and a pair of injection lines **316** according to one embodiment. The heater **302** melts a first composite **230** and a second composite **234** and the pump **304** pressurizes and forces the melted first and second composites **230**, **234** through the injection lines **316**, and into the mold **312** via connection ports **320**. The pump **304** is capable of producing high fluid pressures which permit the first and second composites **230**, **234** to be injected into the mold **312** at high pressures and speeds. Each injection line **316** engages one of the connection ports **320** on the mold **312** such that the first and second composites **230**, **234** can enter the mold **312** at different locations. In some embodiments of system **300**, more than two composite materials can be injected into the mold **312**. In these configurations, the injection molding system **300** can include separate injection lines **316** for each material and the mold **312** may contain separate connection ports **320** for each additional injection line **316**.

When solidified, the first and second composite materials **230**, **234** of FIG. 4 are suitable for formation of a final component, e.g., the instrument panel substrate **120**, reinforcement **150**, component **250**. The first composite **230** includes the first fiber material **258** within the first resin **262**. Similarly, the second composite **234** includes the second fiber material **270** within the second resin **274**. Accordingly, the first and second fiber materials **258**, **270** and the first and second resins **262**, **274** may be composed of any of the respective fibers and resins disclosed in conjunction with the instrument panel substrate **120**, the reinforcement **150**, or the component **250**.

Again referring to FIG. 4, the mold **312** has an A-plate **324** and a B-plate **328**, each plate defining approximately half of a cavity **332** of the mold **312**. The A-plate **324** includes the connection ports **320** through which the first and second composite materials **230**, **234** enter the mold **312**. The A- and B-plates **324**, **328** each contain an impression of one half of the final vehicular component (e.g., vehicular component **250**, substrate **120**, reinforcement **150**, etc.) such that when the mold **312** is closed, the negative impressions define the mold cavity **332** with the approximate dimensions of the final component. In some embodiments, the mold **312** may include inserts and/or subassemblies to aid in formation of the final component.

As shown in FIG. 5A, the mold **312**, when configured to form a substrate **120**, has a driver-side portion **336**, a center-stack portion **340**, and a passenger-side portion **344** oriented to form the respective portions **184**, **180**, **188** of the substrate **120** (FIG. 2). During injection of the melted first and second composites **230**, **234**, a pressure is exerted on the mold **312** such that the A-plate **324** and the B-plate **328** are forced together. The force acting on the mold **312** prevents mold separation and flashing from occurring on the substrate **120**. The mold **312**, while depicted in a closed state in FIG. 5A, may be opened by separating the A-plate **324** and the

B-plate 328. While the mold 312 is in an open state, the substrate 120 may be ejected, and the mold 312 and cavity 332 can then be cleaned. The injection molding system 300 employing mold 312 may also be used in a like manner as described above to form the reinforcement 150, the plenum bracket 220, the vehicular component 250, or a variety of other vehicle components suitable for being fabricated with hybrid composites.

Referring now to FIG. 6, a schematic of a method 360 configured for formation of a final component, such as the substrate 120 of the instrument panel 26, is provided. The method 360 includes five primary steps, steps 364, 368, 372, 376, and 380. The method 360 begins with step 364 of melting the first and second composites 230, 234, followed by step 368 of preparing the injection molding system 300. Next, the step 372 of injecting the first and second melted composite materials 230, 234 into the cavity 332 of the mold 312 is performed. The step 376 of cooling the melted first and second composites 230, 234 to form the final component, e.g., substrate 120 of the instrument panel 26, is conducted next. Finally, the step 380 of removing the final component from the mold 312 is performed.

Referring to FIGS. 4-6, step 364 involves heating the first and second composites 230, 234 in the heater 302 to a temperature sufficient to melt the resin constituents. With the resins melted, the pump 304 is able to push the melted first and second composites 230, 234 through the injection lines 316 and into the cavity 332 of the mold 312 via the connection ports 320. The first and second composites 230, 234, particularly when comprising nylon resin, can be injected at a temperature between 100° C. and 400° C., and more preferably between 210° C. and 275° C. The melted first and second composites 230, 234 typically are superheated to a sufficiently high temperature to prevent their premature solidification in the injection lines 316 before reaching the cavity 332. As used herein, the term “superheat” refers to the temperature difference between the melting temperature and the injection temperature of the first and second composites 230, 234. The superheat is also necessary to ensure that the first and second composites 230, 234 have sufficiently low viscosity to enter narrow areas of the cavity 332. The superheat may be between 10° C. and 50° C. for composites 230, 234. Other injection temperatures and superheat conditions may be appropriate depending on the compositions selected for the composites 230, 234, geometry of the mold 312, and other conditions.

Step 368 of preparing the injection molding system 300 may include tasks such as preheating the mold 312, priming the injection lines 316, and/or placing a preassembled fiber mat or multiple mats into the cavity 332 of the mold 312. Step 372 of injecting the first and second composites 230, 234 may have a duration of between 5 seconds and 30 seconds, and more preferably between 10 seconds and 20 seconds. Other durations may be appropriate for more complex mold cavity 332 geometries and/or lower melt viscosity compositions for the composites 230, 234. In some embodiments, the injection of the melted first and second composites 230, 234 may be simultaneous, while in other embodiments, each composite is injected separately. During the injection step 372, the melted first and second composites 230, 234 are injected into respective driver-side and passenger-side portions 336, 344 of the mold 312 (see FIG. 5A), thereby causing substantial segregation of the fibers in the final component, e.g., substrate 120. The composites 230, 234 may also be injected at other points in the cavity 332 to create the desired segregation or other properties.

Referring again to FIGS. 4-6, step 376 of cooling the melted first and second composites 230, 234 to form the final component, e.g., substrate 120, occurs while the mold 312 is held under pressure and chilled. The mold 312 may be water chilled or may be air chilled to promote solidification of the final component. After solidification of the substrate 120, the mold is opened and step 380 of removing the final component is carried out by actuating a series of ejection pins (not shown) to eject the final component from the B-plate 328 of the mold 312.

With particular reference to FIG. 5A, a cross section of the mold 312 configured to produce the substrate 120 is depicted during the step 372 of injecting the first and second composite materials 230, 234 into the cavity 332 of the mold 312. The first and second composites 230, 234 are injected through a series of gates (not shown). The cavity 332 may be filled by injection of the first and second composites 230, 234 into respective driver-side and passenger-side portions 336, 344 of the cavity 332. Upon entering the mold 312, the melted first and second composites 230, 234 fluidly flow through the cavity 332 toward each other.

Referring now to FIG. 5B, at a predetermined location in the cavity 332, the melted first and second composites 230, 234 continue to flow toward each other to combine to form the boundary region 240. The boundary region 240 includes a mixture of fibers and resins from the first and second composites 230, 234 and may have a width between 1 mm and 50 mm. The location and width of the boundary region 240 is controlled through design of the mold 312, processing parameters of the injection molding system 300 and the particular composition selected for the first and second composites 230, 234. The processing parameters may be controlled by the controller 308 (FIG. 4). In one exemplary embodiment, more than two composite materials having different compositions may be injected into the cavity 332 during the injection step 372. In this configuration, there can be a boundary region 240 between each of the composite materials such that each boundary region 240 has a different composition from the others. Upon cooling and solidification of the first and second composites 230, 234, the mixture of the resins and fibers within the boundary region 240 creates an integral connection between the first composite material 230 and the second composite material 234, thereby holding the substrate 120 or other final component together.

It is to be understood that variations and modifications can be made on the aforementioned structure without departing from the concepts of the present invention. For example, the present disclosure of a hybrid composite and its method of manufacture could be equally applied to the grille of a motor vehicle. Attachment points in a hybrid composite grille, for example, may require added reinforcement in the form of chopped carbon fibers. Further, it is to be understood that such concepts are intended to be covered by the following claims unless these claims by their language expressly state otherwise.

What is claimed is:

1. A vehicular instrument panel, comprising:

a panel element comprising chopped carbon and glass fibers having a length of about 5 to 7 mm within a nylon resin,

wherein the fibers are segregated such that the carbon and glass fibers are each concentrated within respective driver-side and passenger-side portions of the element, and

the panel element comprises a boundary region having a substantially aligned mixture of the carbon and glass fibers in one of the portions.

11

2. The vehicular instrument panel of claim 1, wherein the chopped carbon fibers in the panel element have a fiber volume fraction in the nylon resin of about 15% to about 40%.

3. The vehicular instrument panel of claim 1, wherein the chopped carbon fibers in the driver-side portion of the panel element have a fiber volume fraction of about 30% to 40% in the nylon resin, the chopped glass fibers in the passenger-side portion have a fiber volume fraction of about 30% to 40% in the nylon resin, and each of the chopped carbon and glass fibers in the boundary region have a fiber volume fraction of about 15% to 20% in the nylon resin.

4. A vehicular component, comprising:

a first portion comprising chopped glass fibers within a first resin;

a second portion comprising chopped carbon fibers within a second resin; and

a plurality of boundary regions, each between the portions and having a substantially aligned mixture of the fibers within the first and second resins,

wherein the component is inside or on a vehicle and the fibers have a length of about 5 to 7 mm.

5. The vehicular component of claim 4, wherein each of the first and second resins is selected from the group of

12

materials consisting of a nylon, a polypropylene, an epoxy, a polyester, a vinyl ester, a polyetheretherketone, a poly(phenylene sulfide), a polyetherimide, a polycarbonate, a silicone, a polyimide, a poly(ether sulfone), a melamine-formaldehyde, a phenol-formaldehyde, and a polybenzimidazole.

6. The vehicular component of claim 4, wherein the first and second resins have substantially the same composition.

7. The vehicular component of claim 4, wherein each of the first and second portions of the component has a fiber volume fraction of the respective carbon and glass, chopped fiber materials in the respective first and second resins of about 15% to about 40%.

8. The vehicular component of claim 7, wherein the carbon fiber material in the first portion has a first fiber volume fraction of about 30% to 40% in the first resin, the glass fiber material in the second portion has a second fiber volume fraction of about 30% to 40% in the second resin, and each of the carbon and glass fiber materials in each of the boundary regions has a fiber volume fraction of about 15% to 20% in the first and second resins.

* * * * *